



F550 TMCP toughcore

Cost reduction and increased safety for offshore CO₂ and LPG tank manufacturing

Qualified by DNV and BV, F550 TMCP toughcore offers excellent toughness properties and highest uniform elongation values to increase safety for CO₂ or LPG offshore tank manufacturing.

The outstanding CTOD properties and the remarkable fracture arrest behavior of the base material of F550 TMCP toughcore offers a safety margin which allows even for a fracture mechanic qualification at design temperature and in the heat affected zone.

Even in the unlikely event of full depressurization of your tank, stable toughness values are achieved at temperature of -80 °C or below.

Compared to conventional steel grades, suitable for CO₂ or LPG tank manufacturing, F550 TMCP toughcore offers essential cost savings due to its reduced nickel content.

As a consequence of the sustainable alloying concept, even the CO₂ footprint of your project can be improved.

Convincing advantages

- » Reduced nickel content
- » Cost reduction
- » Reduced CO₂ footprint
- » Best weldability
- » Excellent toughness in combination with high strength
- » Higher safety margin



Premium quality
with reduced carbon footprint

toughcore®
greentec steel

Chemical composition

Heat analysis in mass % acc. standard

Steel grade	Plate thickness [mm]	C max.	Si max.	Mn max.	P max.	S max.	Al max.	Cr max.	Mo max.	Ni max.	Nb max.	Ti max.	CE ¹⁾ max.	PCM max.
F550 TMCP toughcore	≤ 60	0.08	0.5	1.6	0.01	0.005	0.035	0.2	0.43	0.55	0.03	0.015	0.48	0.22

¹⁾ Max. 0.50 for WT exceeding 50 mm

Mechanical properties: Notch impact energy ²⁾

Values in as-delivered condition acc. standard

Steel grade	Test temperature [°C]	Test location [mm]	Notch impact energy	
			Testing direction transversal	A min. [J]
F550 TMCP toughcore	-80	¼ thickness	50	35
	-60	½ thickness		

²⁾ Testing will be carried out in transverse direction acc. to DNVGL Rules for Classification – Ships, Part 2 respectively DNVGL OS-B101. Additional testing in the simulated stress relieved condition can be agreed at a temperature of max. 580 °C.

Mechanical properties: Tensile test ³⁾

Values in as-delivered condition acc. standard

Steel grade	Yield strength R _{p0.2} [MPa] min. t = 20 ≤ 60 mm	Tensile strength R _m [MPa]			Fracture elongation A5 L ₀ = 5.65 √ S ₀ [%] min. t = 20 ≤ 60 mm	Uniform elongation [%] min. t = 20 ≤ 60 mm	Ratio max.
		t ≤ 42 mm	t > 42 ≤ 50 mm	t > 50 ≤ 60 mm			
F550 TMCP toughcore	550	670 – 830	660 – 830	650 – 830	19	7	0.9

³⁾ Testing will be carried out in transverse direction acc. to DNVGL Rules for Classification – Ships, Part 2 respectively DNVGL OS-B101. Additional testing in the simulated stress relieved condition can be agreed at a temperature of max. 580 °C. Yield strength ratio of max. 0.87 upon request.

Welding Pre-Qualification ⁴⁾

Pre-Qualification	Welding process	Test location	Test temperature [°C]
CTOD	SAW 1.5 & 2.5 kJ/mm	FL / FL + 1 mm	min. 0.2 mm / -35
CVN			-60
CTOD	SAW 5.0 kJ/mm	FL / FL + 1 mm	min. 0.2 mm / -10
CVN			-60

⁴⁾ Additional testing in the simulated stress relieved condition can be agreed at a temperature of max. 580 °C.

Available dimensions

Steel grade	Plate thickness [mm]	Max. width [mm]	Max. length [mm]	Max. weight [t]	As-delivered condition
F550 TMCP toughcore	≤ 60	3,850	18,000	21.5	toughcore®

Additional dimensions upon request.

OUR PATH TO A GREENER FUTURE

Premium products in the greentec steel Edition

With greentec steel, voestalpine is pursuing an ambitious step-by-step plan in the long-term decarbonization of steel production. The declared objective is to achieve carbon-neutral production by 2050, and the initial steps have already been taken. Process-optimized production operations already prevent up to 10% of the direct CO₂ emissions at the Linz site. The material and processing properties of the steel are not affected in any way in this production route. Each voestalpine heavy plate product is available in premium quality in the greentec steel Edition with a reduced carbon footprint and unique benefits.



Premium quality with reduced carbon footprint

toughcore®
greentec steel

Heavy plates (excl. heads and clad plates) – greentec steel Edition

Max. carbon footprint 2.35 kg CO₂e per kg of steel ¹⁾

¹⁾ per EN 15804+A2 (EPD methodology) cradle to gate

The information and product properties contained in this printed material are non-binding and serve the sole purpose of technical orientation. They do not replace individual advisory services provided by our sales and customer service teams. The product information and characteristics set forth herein shall not be considered as guaranteed properties unless explicitly stipulated in a separate contractual agreement. For this reason, voestalpine shall not grant any warranty nor be held liable for properties and/or specifications other than those subject to explicit agreement. This also applies to the suitability and applicability of products for certain applications as well as to the further processing of materials into final products. All application risks and suitability risks shall be borne by the customer. The General Terms of Sale for Goods and Services of the voestalpine Steel Division shall apply to all materials supplied by the voestalpine Steel Division and can be accessed using the following link: www.voestalpine.com/stahl/en/The-Steel-Division/General-Terms-of-Sale

Technical changes are reserved. Errors and misprints are excepted. No part of this publication may be reprinted without explicit written permission by voestalpine Stahl GmbH.